ALUMINIUM STEARATE

TRADEASIA

General Information

Chemical Formula	$Al(C_{17}H_{35}COO)_3$	$Al(C_{17}H_{35}COO)_3$
Synonym	Aluminium tristearate	
Origin	China	
H.S. Code	2915.70.90	
CAS No.	637-12-7	
Molecular Weight	844.41 g mol^{-1}	

Application

Production	Aluminium Stearate is used as a lubricant in the production of polyamides and thermosetting plastics.
Varnish production	It is used as a thickening agent in the production of varnishes and lacquers.
Repellent agent	It is also used as a water repellent agent and hydrophobic agent.

Property	Units	Value
Appearance		White powder
Al_2O_3 Content	%	10.0 ± 1.0
Melting point	°C	150 (min)
Moisture	%	3.0 (min)
Free fatty acids	%	4.0 (max)
Fineness	%	1.0 (max)
Solubility in water		Insoluble
Stability		Stable under ordinary conditions

Packaging

- 1250 @ 20 kg PP/PE Bags, 25 MT / 20'FCL

Tradeasia International Pte Ltd
133 Cecil Street # 12-03 Keck Seng Tower
Singapore 069535
Republic Of Singapore
Tel: +65 6227 6365
Fax: +65 6225 6286
Email: contact@chemtradeasia.com